



Product code : 34018A

EMFICOL 34018A

DESCRIPTION

EMFICOL 34018A is a solvent-based polyurethane adhesive.

AREAS OF APPLICATION

EMFICOL 34018 is especially used for bonding plasticized PVC foils on themselves.

TECHNICAL DATA

Colour	Slightly milky
Viscosity	Brookfield RVT / spindle 4 / 10 rpm : 9,000 ± 3,000 mPa.s
Density at 20 °C	0.85 ± 0.02
Conventional solids content (EN 827)	16 ± 2 %
Temperature resistance of the assemblies	Ca. 80 °C without hardener / 100 to 120 °C with 4 % hardener D0024A
Cleaner	EMFINET 684/5 before setting
Specific data	Pot life at 20 °C : ca 2 h with 4 % hardener D0024A

ADVICE

See also material safety data sheet of hardener.

INSTRUCTIONS FOR USE

Substrates preparation :

The substrates to be assembled must be dry, dust free and not have any traces of grease or other contaminants that could adversely affect the bonding performance.

If the substrates need to be cleaned, use EMFINET 688/1 or alcohol.

Check the compatibility of the solvent used with the substrates.

When using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by the manufacturer or supplier.

Application :

Coat the foils with a regular layer of EMFICOL 34018A with a brush or a roller.

Often, coating of only one of both foils to be bonded is sufficient. The types of PVC being various, it is advised to check if one or both foils have to be coated.

Let dry about 10 minutes and heat reactivate between 80 and 90 °C.

Apply precisely both parts at this temperature (once both substrates are assembled, they can't be repositioned or separated) and press briefly but firmly.

First setting is high ; definitive setting is reached after 24 hours.

In order to ensure high water and heat resistance, add 4 % of hardener D0024A (see table above).

Cleaning :

Tools can be cleaned with EMFINET 684/5 or acetone.

In case of use with hardener, abrasion could be necessary after curing.



CONSUMPTION

Ca 200 g/m²

STORAGE AND SHELF LIFE

12 months between 5 and 25 °C in closed original packaging.

PACKAGING

Metal packagings : 750 mL metal boxes ; 18.5 kg metal cans ; 170 kg metal drums

SAFETY

Highly flammable and irritant. Read material safety data sheet before use.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.