



Product code : 50040A

ISOLEMFI 3300

Water resistant according to standard EN 204-D4

DESCRIPTION

ISOLEMFI 3300 is a one-part polyurethane-based moisture curing adhesive.

AREAS OF APPLICATION

ISOLEMFI 3300 may be used for bonding of hard insulating foams like extruded or expanded polystyrene and phenolic foam or of panels from mineral wool on wood, plaster boards (with or without vapour shield), fibre-cement, steel sheets for production of partition walls and thermic insulation elements.

For difficult materials (galvanized steel, raw aluminium, polyester, PVC...), it is necessary to make tests beforehand.

TECHNICAL DATA

Appearance	Thixotropic paste
Colour	Milky
Viscosity at 20 °C	Brookfield RVT 7, speed = 5 rpm : 400,000 ± 100,000 mPa.s
Density at 20 °C	1.05 ± 0.02
Conventional solids content (EN 827)	> 99 %
Open time at 20 °C	5 min
Pressing time at 20 °C	1 h
Final setting time at 20 °C	24 h
Temperature resistance of the assemblies	-30 to +100 °C
Cleaner	EMFINET 683 before setting
Specific data	Water resistance : very good

ADVICE

See also material safety data sheet



INSTRUCTIONS FOR USE

The substrates to be assembled must be flat, dry, dust free and not have any traces of grease or other contaminants that could adversely affect the bonding performance.

If the substrates need to be cleaned, methyl ethyl ketone (MEK) may be used. The use of solvents must comply with local regulations. Check the compatibility of the solvent used with the substrates. If necessary, rub down metal surfaces beforehand.

When using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by the manufacturer or supplier of this type of product.

The adhesive is applied to one of the surfaces to be bonded by a manual or pneumatic gun or with a serrated spreader. One of the materials to be bonded must be porous or contain moisture.

If both substrates are non porous, it is imperative to spray a light water mist (10 to 15 g/m²) onto the adhesive film. Assembling has to be followed by a uniform and maximum pressure applied across the entire surface without irreversible deformation of substrates.

The setting time depends on hydrometry and temperature. So, it is necessary :

- in case of working under 20° C : to be sure that the pressing time is long enough

- in case of working over 20° C : to be sure that open time and closed assembly time are not excessive

Otherwise, defective bonding could happen.

If necessary, refer to our technical service.

CONSUMPTION

150 to 250 g/m² according to the method of application and the materials to be bonded.

STORAGE AND SHELF LIFE

12 months in closed original packaging stored in dry premises between 5 and 25 °C

PACKAGING

310 mL cartridges

SAFETY

Harmful. See Material Safety Data Sheet.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application.

Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.