



Product code : 50061C

ISOLEMFI 50061C + HARDENER 521

DESCRIPTION

Polyurethane two parts adhesive.

AREAS OF APPLICATION

ISOLEMFI 50061C mixed with hardener 521 can be used for bonding of hard insulating foams like extruded or expanded polystyrene and phenolic foam or of panels from mineral wool on plaster boards (with or without vapour shield), fibre-cement, steel sheets, aluminium for production of partition walls and thermic insulation elements.

TECHNICAL DATA

	PART A	PART B
	ISOLEMFI 50061C	HARDENER 521
Type of product	Based upon polyethers	Isocyanates
Colour	Beige	Dark brown
Viscosity at 20 °C	Brookfield RVT / spindle 5 / 10 rpm: 18,000 ± 8,000 mPa.s	Brookfield LVT / spindle 2 / 30 rpm : 250 ± 100 mPa.s
Density at 20 °C	1.42 ± 0,04	1.23 ± 0.02

ADVICE

See material safety data sheets of both components.

MIXTURE A + B	
Mixture (in weight)	A/B = 50061C/D0521A = 100/40
Mixture (in volume)	A/B = 50061C/D0521A = 100/50
Application temperature	15 to 30 °C
Open time at 20 °C	1 h
Pressing time at 20 °C	2 h
Final setting time at 20 °C	48 h
Calorific power	Ca. 19.2 MJ/kg
Specific data	Colour : dark beige



INSTRUCTIONS FOR USE

Preparation of materials :

The materials must be flat, dry, dust-free and not have any traces of grease or other contaminants that could adversely affect the bonding performance.

They may be cleaned with EMFINET 683 or methylethylketone (MEK). The use of solvents must comply with local regulations. Check the compatibility of the solvent used with the substrates.

If necessary, rub down metal surfaces beforehand. Clean them after rubbing down.

Let dry after degreasing.

When using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by the manufacturer.

Application :

It is recommended to work at a temperature between 15 and 30 °C.

Pour part B (hardener) into part A and mix in order to get a homogeneous mixture.

Apply this mixture uniformly with a roller or a scraper to one of the substrates on its whole surface.

Press during setting to ensure a perfect contact between substrates and adhesive.

To specify the times, see the paragraph titled "Technical data".

The setting speed is slower at low temperature and quicker at high temperature.

So, it is necessary :

- in case of working under 20 °C : to be sure that pressing time is long enough

- in case of working over 20 °C : to be sure that open time and closed assembly time are not excessive. Otherwise defective bonding could happen.

Cleaning :

Tools should be cleaned with EMFINET 683, MEK or acetone before the adhesive has completely cured. After curing, abrasion is necessary.

CONSUMPTION

200 to 300 g/m² depending on materials

STORAGE AND SHELF LIFE

In closed original packaging stored in dry premises between 5 and 25 °C :

ISOLEMFI 50061C : 9 months

HARDENER 521 : 12 months

PACKAGING

Metal packagings

SAFETY

50061C : not classified as hazardous. Hardener 521: harmful

Read material safety data sheet before use.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.