



Product code : 75007D

EMFIMASTIC JOINT DE PARQUET

DESCRIPTION

EMFIMASTIC JOINT DE PARQUET is a single component elastomeric MS sealant without isocyanates.

It cures under the effect of atmospheric humidity to form a flexible and resistant joint.

EMFIMASTIC JOINT DE PARQUET can be coated with finish products (oil-based, varnish).

The surface after sanding is perfect (without microbubbles).

AREAS OF APPLICATION

EMFIMASTIC JOINT DE PARQUET is used for parquet joints in bathrooms.


This sealant can be applied without any primer on all kinds of wood parquet floors.

TECHNICAL DATA

Appearance	Pasty
Colour	Black
Density at 20 °C	1.54 ± 0.05
Sagging (ISO 7390)	< 2 mm
Application temperature	5 to 35 °C
Skin formation time at 23 °C and 50 % HR	20 ± 10 min
Cure time at 23 °C and 50 % HR	> 3 mm/24 h
Final Shore A hardness (ISO 868 - 3 seconds)	50 ± 5
Volume loss (ISO 10563)	< 2 %
Temperature resistance	-40 to + 100 °C
UV resistance	Excellent
Compatibility with paints	Water based : yes Solvent based : test required
Specific data	Elongation at break (ISO 37) : > 100 % Modulus at 100 % (ISO 37) : ca. 1 MPa Modulus at break (ISO 37) : > 1.8 MPa

ADVICE

See also material safety data sheet



INSTRUCTIONS FOR USE

Substrate preparation :

All traces of oil, grease and poorly adherent paints or coatings should be systematically removed beforehand.

Caulking :

EMFIMASTIC JOINT DE PARQUET can be applied by a pneumatic gun on clean, dust- and grease-free substrates.

After application, each joint can be smoothed out using a damp pastering knife.

Remove quickly all excess sealant.

Wait full setting (about 2 days) before sanding and varnishing or vitrification.

This product should be used within 24 hours of opening the cartridge protection ; otherwise, the sealant could harden inside.

In cold weather, store the cartridges at about 20 °C before use.

Avoid any contact with non-cured polyurethanes during curing.

Cleaning :

Tools can be cleaned with EMFINET 683, MEK or acetone before the sealant has completely cured. After curing, abrasion is necessary.

STORAGE AND SHELF LIFE

12 months in the original, hermetically sealed packagings between 5 and 25 °C

PACKAGING

290 mL cartridges in boxes of 25 units.

SAFETY

Not classified as hazardous. Read the material safety data sheet before use.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.