



Product code : 77006

## EMFIMASTIC ACRYL PARQUET

### DESCRIPTION

EMFIMASTIC ACRYL PARQUET is a high quality acrylic sealant.

### AREAS OF APPLICATION

EMFIMASTIC ACRYL PARQUET is specially recommended for finishing joints between walls and skirtings, parquets, laminated floorcoverings and walls.


EMFIMASTIC ACRYL PARQUET adheres perfectly to most usual building materials.

### TECHNICAL DATA

Appearance	Pasty
Colour	Maple, clear oak, middle oak, dark oak, cherry-wood, red wood, light grey, wenge
Density at 20 °C	1.65
Application temperature	10 to 30 °C
Temperature resistance of the assemblies	-30 to +100 °C
Cleaner	Water before setting
Specific data	Skin time formation (superficial setting) at 23 °C and 50 % RH: 60 to 70 min Shore A hardness (ISO 868 - 3 seconds) : 33 Modulus at 100 % elongation (ISO 8340) : 0.8 daN/cm <sup>2</sup> Elongation at break (ISO 8339) : > 250 % Elastic recovery (ISO 7389) : < 50 % Maximum deformation : 15 %

### ADVICE

See also material safety data sheet



### INSTRUCTIONS FOR USE

#### Substrates preparation :

The substrates to be assembled must be dry, dust free and not have any traces of grease or other contaminants that could adversely affect the bonding performance.

Clean them if necessary with alcohol or methylethylketone (MEK).

Allow the substrate to dry after degreasing.

Adhesion tests prior to the application are recommended.

#### Application :

EMFIMASTIC ACRYL PARQUET can be applied with a manual or pneumatic gun.

After application, use a wet putty knife to smooth the joint.

EMFIMASTIC ACRYL PARQUET can be sanded after 48 h.

#### Cleaning :

Tools can be cleaned with water before drying of the sealant. After drying, abrasion is necessary.

#### Compatibility with paints, varnishes and oils :

EMFIMASTIC ACRYL PARQUET may be coated after full setting (1 to 2 weeks).

A compatibility test is necessary before application of a covering layer.

#### STORAGE AND SHELF LIFE

12 months in unopened original packaging stored between 5 and 25 °C. Protect from frost.

#### PACKAGING

Carton boxes containing 12 cartridges of 310 mL

#### SAFETY

Not classified as hazardous. Read material safety data sheet.

#### PRECAUTIONS FOR USE

Outside application must not be made under rain.

Do not expose joints to continuous contact with water.

A maximum movement of 5 % is allowed during the first days of drying.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.