



Product code : D0004A

HARDENER 500AE

DESCRIPTION

HARDENER 500AE is a triisocyanate dissolved in ethyl acetate.

AREAS OF APPLICATION

HARDENER 500AE can be used with some polychloroprene adhesives in order to increase adhesion especially on rubber, and to increase heat and water resistance.

TECHNICAL DATA

Colour	Green-yellowish or brown-reddish to dark violet ; colour has no influence on product quality
Viscosity	Brookfield LVT / spindle 1 / 60 rpm : ca 3 mPa.s
Density at 20 °C	Ca 0.99
Conventional solids content (EN 827)	Ca 27 %
Specific data	Isocyanate content : 9.3 ± 0.2 %

ADVICE

See also material safety data sheet

INSTRUCTIONS FOR USE

Temperature before mixing has to be between 15 and 25 °C.
See the technical data sheet of the adhesive used (e.g. EMFICOL NO/S).

CONSUMPTION

See the technical data sheet of the adhesive used.

STORAGE AND SHELF LIFE

12 months in tightly closed original packaging between 5 and 25 °C.
Avoid contact with moisture during pouring.

PACKAGING

50, 200 and 400 mL glass bottles ; 800 g metal bottles ; 1,000 g cans

SAFETY

Harmful and highly flammable. See material safety data sheet before use.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product

is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.