



Product code : D0008A

## HARDENER DA

### DESCRIPTION

Polyisocyanate.

### AREAS OF APPLICATION

HARDENER DA allows to improve water resistance of bonded wood assemblies made with EMFIBOIS 863.

These assemblies made according to standard EN 205 are water resistant according to standard EN 204-D4.

### TECHNICAL DATA

Colour	Clear, slightly yellowish
Viscosity	Ca 300 mPa.s
Density at 20 °C	1.13
Conventional solids content (EN 827)	100 %
Cleaner	Water before cross-linking

### ADVICE

See also material safety data sheet



### INSTRUCTIONS FOR USE

See technical data sheet of EMFIBOIS 863 (code number : 086300)

Observe the stated mixing ratio.

Be careful not to exceed pot life. It can't be evaluated according to mixture appearance because viscosity doesn't increase noticeably even after full reaction of the hardener.

### STORAGE AND SHELF LIFE

12 months in tightly closed original packaging between 5 and 25 °C.

Do not expose to freezing.

### PACKAGING

500 g bottles

### SAFETY

Irritating. See material safety data sheet before use.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.