



Product code : D0021A

ACCELERATOR D0021A

DESCRIPTION

Aminated catalyst.

AREAS OF APPLICATION

ACCELERATOR D0021A is designed to increase the setting speed of one component polyurethane adhesives.

TECHNICAL DATA

Colour	Colourless
Viscosity	Very fluid
Density at 20 °C	1.01 ± 0.01
pH	10 ± 0.2
Conventional solids content (EN 827)	Ca 6 %

ADVICE

See also material safety data sheet

INSTRUCTIONS FOR USE

Application :

Spray a thin mist of accelerator D0021A with a pneumatic gun on the adhesive film.

Open time is very short (a few ten-seconds or a few minutes).

So it is necessary to be sure that open time and closed assembly time are not excessive before pressing. Otherwise, defective bonding could happen.

Refer to the technical data sheet of the one component polyurethane adhesive used.

Cleaning :

Tools can be cleaned with water.



CONSUMPTION

10 to 15 g/m²

STORAGE AND SHELF LIFE

6 months in closed original packaging stored in dry premises between 5 and 25 °C. Not frost resistant.

SAFETY

Not classified as hazardous. Read material safety data sheet.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.