



Product code : D0024A

## HARDENER D0024A

### DESCRIPTION

HARDENER D0024A is based on polyisocyanates and organic solvents

### AREAS OF APPLICATION

HARDENER D0024A can be mixed with all solvent-based polyurethane systems used especially in shoes and leather industry to get a better adhesion on rubber, and to improve heat and water resistance.

### TECHNICAL DATA

Colour	Brown
Viscosity	Very fluid
Density at 20 °C	0.96 ± 0.02
Conventional solids content (EN 827)	27 ± 2 %
Specific data	Pot life : ca 20 h at 20 °C (depends of the adhesive used) Isocyanate content : ca 8 %

### ADVICE

See also material safety data sheet

### INSTRUCTIONS FOR USE

Homogeneously mix both parts (average ratio : 4 % of hardener).  
See technical data sheet of the adhesive used.



### STORAGE AND SHELF LIFE

12 months in tightly closed original packaging between 5 and 25 °C

### PACKAGING

800 g aluminium bottles

### SAFETY

Highly flammable and harmful. See material safety data sheet before use.

### PRECAUTIONS FOR USE

Be careful not to exceed pot life.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.