



Product code : D0521A

## HARDENER 521

### DESCRIPTION

Mixture of isomers of diphenylmethane diisocyanate.

### AREAS OF APPLICATION

HARDENER 521 can be used for increasing water and temperature resistance of some polyurethane adhesives.


### TECHNICAL DATA

	PART A	PART B
Colour		Dark brown
Viscosity at 20 °C		Brookfield LVT / spindle 2 / 30 t/min : 250 ± 100 mPa.s
Density at 20 °C		1.23 ± 0.02
Conventional solids content (EN 827)		100 %
Cleaner		EMFINET 683

MIXTURE A + B	
Temperature resistance of the assemblies	See technical data sheet of the adhesive used (part A)

### ADVICE

See also material safety data sheet



### INSTRUCTIONS FOR USE

Homogeneously mix both parts together.  
Be careful not to exceed pot life.  
See technical data sheet of the adhesive used.

### STORAGE AND SHELF LIFE

12 months in tightly closed original packaging between 5 and 25 °C

## PACKAGING

120 g glass flasks ;  
1,000 metal flasks ;  
600 g metal boxes ;  
1.2, 1.5, 2, 4, 5, 20 and 30 kg metal cans.

## SAFETY

Harmful. See material safety data sheet before use.

## PRECAUTIONS FOR USE

After opening of packaging, it is necessary to protect the product from humidity.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.