



Product code : X2413A

EMFICOL X2413A

DESCRIPTION

EMFICOL X2413A is a brushable contact adhesive based on polychloroprene rubber and synthetic resins in organic solvents.

AREAS OF APPLICATION


EMFICOL X2413A can be used for bonding a lot of materials (laminated panels, some rubbers, some hard plastics, leather, wood, veneering, chipboards, fibrecement, plywood, cork, mineral wool, PU foams, metals on themselves or each other according to the case). For difficult materials, it is necessary to make tests beforehand.

TECHNICAL DATA

Colour	Light brown
Viscosity	Brookfield RVT / spindle 3 / 20 rpm : ca. 1,600 mPa.s
Density at 20 °C	0.91 ± 0.02
Conventional solids content (EN 827)	21 ± 1 %
Application temperature	10 to 30 °C
Open time at 20 °C	30 min
Temperature resistance of the assemblies	Maximum 120 °C on panels
Final setting at 20 °C	2 to 3 d
Cleaner	EMFINET 695

ADVICE

See also material safety data sheet



INSTRUCTIONS FOR USE

Substrates preparation :

The substrates to be assembled must be dry, dust free and not have any traces of grease or other contaminants that could adversely affect the adhesive performance.

Clean the substrates with methylethylketone (MEK), EMFINET 695 (or EMFINET 688/1 for materials sensitive to ketones). Solvents must comply with local regulations. Check the compatibility of the solvent used with the substrates. When using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by the manufacturer.

If necessary, rub down metal surfaces beforehand and clean them. Let dry after degreasing. Temperature of adhesive and substrates have to be between 10 and 30 °C.

Application :

Apply a regular layer of EMFICOL X2413A with a brush or a notched spreader on each substrate. Let solvents evaporate (5 to 15 minutes depending on temperature, hygrometry and substrates).

Take care not to exceed open time ; otherwise, bonding will be defective.

Apply precisely both parts and press firmly and evenly on the whole surface.

Code produit : X2413A - édition du 07-12-2007
3 rue Ettore Bugatti - 67500 Haguenau
Tél : 03 88 90 60 00 - Fax : 03 88 73 48 38
Internet : <http://www.emfi.com> - Mél. : emfi@emfi.com
Rédacteur : AC

Once the two substrates are assembled, they can't be repositioned or separated.

Cleaning :

Tools can be cleaned with EMFINET 695 or MEK.

CONSUMPTION

100 to 150 g/m² on each surface depending on substrates. For very porous materials, a higher amount may be necessary.

STORAGE AND SHELF LIFE

12 months between 5 and 25 °C in closed original packaging.

PACKAGING

Metal packagings

SAFETY

Highly flammable and irritant. Read material safety data sheet before use.

PRECAUTIONS FOR USE

EMFICOL X2413A can't be used for bonding expanded polystyrene, polyethylene, polypropylene, fluorinated polymers and is not recommended for bonding plasticised PVC.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.